

Test Monitoring Center

Carnegie Mellon University 6555 Penn Avenue, Pittsburgh, PA 15206, USA http://astmtmc.cmu.edu 412-365-1000

MEMORANDUM: 13-029

DATE: May 17, 2013

TO: Leonard Orzech,

Chairman, Ball Rust Test Surveillance Panel

FROM: Michael T. Kasimirsky Michael J. Rasimisky


SUBJECT: BRT Testing from October 1, 2012 through March 31, 2013

A total of 129 BRT tests were reported to the Test Monitoring Center during the period from October 1, 2012 through March 31, 2013. Following is a summary of testing activity this period.

	Reporting Data
Number of Labs	4

Tests reported this period were distributed as shown below:


NUMBER OF TESTS REPORTED BY LAB AND REPORT PERIOD



Test Distribution by Oil and Validity

					Totals		
		1006	81	82	This Period	Last Period	
Accepted for Calibration	AC	28	64	34	126	121	
Hardware Qualification Run	NI	0	0	0	0	0	
Unacceptable for Calibration	OC	0	0	0	0	1	
Operationally Invalid (lab)	LC	0	1	0	1	0	
Operationally Invalid (lab/TMC)	RC	0	0	0	0	0	
Aborted Calibration	XC	0	2	0	2	3	
Total		28	67	34	129	125	

OPERATIONALLY VALID TESTS MEETING ACCEPTANCE CRITERIA



The above chart shows the percentage of accepted operationally valid tests. No tests failed to meet the acceptance criteria this period.

Lost Tests per Start by Lab and Oil

		1006		81		82			Total			
Lab	Lost	Starts	%	Lost	Starts	%	Lost	Starts	%	Lost	Starts	%
A	0	13	0	0	29	0	0	15	0	0	57	0
В	0	6	0	1	16	6	0	7	0	1	29	3
D	0	1	0	0	1	0	0	3	0	0	5	0
G	0	8	0	2	21	10	0	9	0	2	38	5
Total	0	28	0	3	67	4	0	34	0	3	129	2

Lost tests are those that were aborted or operationally invalid. Three tests were lost this period.

Causes for Lost Tests

			Oil		Validity			Loss Rate			
Lab	Cause		1006	81	82	LC	RC	XC	Lost	Starts	%
В	Power Failure			•				•	1	129	1
C	Power Failure			•				•	1	129	1
G	Computer Failure			•		•			1	129	1
		Lost	0	3	0	1	0	2			
		Starts	28	67	34	129	129	129			
		%	0	4	0	1	0	2			

Average Δ /s by Lab

Lab	n	AGVYI
A	57	0.565
В	28	0.589
D	5	1.209
G	36	-0.444
Industry	126	0.308

Individual test results can be found on the TMC Web Page at the following link:

ftp://ftp.astmtmc.cmu.edu/refdata/bench/brt/data/


CUSUM PLOT

BALL RUST TEST INDUSTRY OPERATIONALLY VALID DATA




REFERENCE AVERAGE GRAY VALUE

CUSUM Severity Analysis



POOLED S:

Pooled s for this period is 10.35. Shown below is a bar chart comparing the pooled s values for AGV over the last four report periods.



STATUS OF REFERENCE OIL SUPPLY:

At the end of this report period, the testing oil supply stood as outlined in the following table:

		@ TMC			
Oil	Samples @ Labs	Samples (30 mL)	Gallons		
1006	16	4425	35.4		
81	17	1150	9.2		
82	15	575	4.6		
82-1	8	1225	9.8		
Total	56	7375	59.0		

INFORMATION LETTERS:

No information letters were issued this period.

SUMMARY

- Over the course of this report period, AGV severity as measured by cusum plotting continued the mild trend that has existed since the inception of the test.
- Precision as measured by pooled standard deviation is worse than previous periods but comparable to historical performance.

MTK/mtk/astm0413.doc/mem13-029.mtk.doc

c: F. M. Farber

J. A. Clark

BRT Surveillance Panel

ftp://ftp.astmtmc.cmu.edu/docs/bench/brt/semiannualreports/brt-04-2013.pdf

Distribution: email